













COVERLAM																			
SERIE SERIES	REFERENCIA REFERENCE	UNE-EN ISO 10545-3 AA*	UNE-EN ISO 10545-4 R-F*	UNE-EN ISO 10545-9 R-CH-T*	UNE-EN ISO 10545-5 R-G*	UNE-EN ISO 10545-11 R-C*	UNE-EN ISO 10545-14 M*	UNE-EN ISO 10545-13			UNE-EN ISO 10545-7 PEI*	UNE-EN ISO 10545-6	UNE-EN ISO 10545-12 R-HE*	NORMA DIN 51 130	NORMA ASTM-C1028-96		UNE-ENV 12633/2003	UNE-EN 13501-1	
								A-L*	A-P*	A*/B*					FD	FW			
COVERLAM 3,5mm	BASIC	NEGRO, BLANCO, GRIS, TABACO	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,83	0,80	Clase 1	A2-s1, d0
	CONCRETE	NEGRO, GR, TAB, MARFIL	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,71	0,68	Clase 1	A2-s1, d0
	ESTUARIO	[NATURAL]	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,79	0,74	Clase 1	A2-s1, d0
	LIMESTONE	MARRON, GR, BGE, BL, NE	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,75	0,73	Clase 1	A2-s1, d0
	OXIDO	NEGRO, MARFIL	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,79	0,74	Clase 1	A2-s1, d0
	SUPREME	[NATURAL]	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,79	0,74	Clase 1	A2-s1, d0
	TRAVERTINO	BLANCO, ANTRACITA	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,78	0,66	Clase 1	A2-s1, d0
	WOOD	NOGAL, CEREZO	< 0,3%	> 90 N/mm ²	0,8	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,72	0,68	Clase 1	A2-s1, d0
COVERLAM 5,6mm	BASIC	NEGRO, BLANCO, GRIS, TABACO	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,83	0,80	Clase 1	A1
	ESTUARIO	[NATURAL]	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,79	0,74	Clase 1	A1
	ESTUARIO	[PULIDO]	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULB	-	≤ 175 mm ³	Resiste	-	0,68	0,60	Clase 0	A1
	SUPREME	[NATURAL]	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,79	0,74	Clase 1	A1
	SUPREME	[PULIDO]	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULB	-	≤ 175 mm ³	Resiste	-	0,66	0,60	Clase 0	A1
	TITAN	GRIS, CEMENTO, ANTRACITA	< 0,3%	> 50 N/mm ²	0,7	Resiste	Resiste	5	UA	UA	ULA	-	≤ 175 mm ³	Resiste	R-9	0,83	0,80	Clase 1	A1